

↳ *A BETTER WAY*

Key Attributes:

- Great Optics
- Broad Seal Range
- Good Strength
- Great Seal Initiation Temperature
- Designed for Digital Print Markets

CDE-F

LLDPE / mPE Coextrusion

Typical End Uses: This film is ideal for digital print applications that require film economics and great sealing performance.

Attribute	Typical Value	Units	ASTM Test Method
Gauge	3.50	mil	
Yield @ 1mil	30,000	in ² /lb	
Haze	15	%	D-1003
Gloss (45°)	65	%	D-2457
Tensile	MD	4,100	psi
	TD	3,200	
Elongation	MD	825	%
	TD	950	
Secant Modulus	MD	32,000	psi
	TD	35,000	
Elmendorf Tear	MD	325	g
	TD	1,050	
Dart Impact	350	g	D-1709 (method A)
O ₂ TR	N/A	cc/100in ² /24hr (0% RH, 23°C)	D-1434
MVTR	N/A	g/100in ² /24hr (90% RH, 100°F)	F-1249
Creation Date:			03/13/2017

The information provided is a good faith summary of typical film properties but is not meant to be used as a specification, nor as a guarantee of film properties. Users must assume responsibility for fitness of use in their individual applications. In addition, Charter NEX Films, Inc. does not warranty against patent infringement.