

Technical Data Sheet

KK877

Thermal Transfer Receptive UV Coating



Product Description

KK877 is a benzophenone free, matte UV coating with superior receptivity properties like thermal transfer, foil stamping and other finishing applications. KK877 is typically applied over wet or dry toner and hybrid or UV inks on various paper and nonporous substrates. For additional information regarding assistance and applications, please contact your Kustom Koatings representative.

Performance Characteristics

- BZP (Benzophenone) free
- Excellent adhesion to a wide variety of select plastics
- Excellent rub and chemical resistance
- Low odor and low yellowing
- Thermal transfer receptive, imprintable, foil-stampable, glueable, etc.
- Writable; ball point pen and other permanent marking utensils

Physical Properties

- Viscosity: 38 - 42 sec. #3 Zahn
- Specific Gravity: 1.11
- Solids: > 99%

End Use Considerations

KK877 should be evaluated in the laboratory using the actual ink system and substrate to ensure that leveling, intercoat adhesion, gloss and other performance characteristics are acceptable. In general, UV coatings may not exhibit complete intercoat adhesion over some ink systems. A primer may be considered for use if this property needs to be improved.

Storage and Handling Information

Care should be taken not to expose radiation curable products to temperatures exceeding 100°F for prolonged periods of time or to direct sunlight. Storage must be in a cool, shaded, well-ventilated and dry area. To do otherwise might cause uncontrollable polymerization of the product with generation of heat. Do not store this material under an oxygen-free atmosphere. This material should not be stored for more than six (6) months.

Certain precautions should be taken when handling this product. Please refer to the Safety Data Sheet (SDS) for further details. This product contains materials that may cause moderate skin injury (reddening and swelling) and/or sensitization. Since irritation may not occur immediately, contact can go unnoticed. Consult the SDS for appropriate equipment prior to using this or any other materials referred to in this Technical Data Sheet.

FOR YOUR PROTECTION:

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning uses or applications are only the opinion of Kustom Services, LLC, and users should make their own tests to determine the suitability of this product for their own particular purposes. However, because of numerous factors affecting results, Kustom Services, LLC makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for particular purpose, other than that the material conforms to its applicable current Standard Specifications. Standard Specifications, although current at the time of publication, are subject to change without notice. Please refer to the SDS for additional information.

DATE REVISED: 05/23/2019